










"Durisol" blokų techniniai duomenys	Mato vnt									
izoliacijos tipas							neoporas	neoporas		
Bloko kodas		DM 15/9	Dsi 30/20	DMi 17/12	DMi 20/13	DMi 25/18	DSs 30/12	DSs 37,5/12	SB 50	DM 15/9 DR
Bloko gabaritai: plotis/aukštis/ilgis	cm	15/25/50	30/25/50	17/25/50	20/25/50	25/25/50	30/25/50	37,5/25/50	50/25/50	15/25/50
Bloko masė	kg/vnt	6	11	9	11	12	10	15	18	6
Izoliacijos storis	cm						10,5	17,5	23	9
Tinkuotos sienos šilumos laidumo koef. <b>U (k)</b>	W/m <sup>2</sup> K	1,19	0,64	1,33	1,15	1,07	0,28	0,18	0,11	0,28
Tinkuotos sienos šiluminė varža <b>R</b>	m <sup>2</sup> K/W	<b>0,84</b>	<b>1,56</b>	<b>0,753</b>	<b>0,871</b>	<b>0,937</b>	<b>3,569</b>	<b>5,686</b>	<b>8,923</b>	<b>3,56</b>
Tinkuotos sienos garso varža <b>Rw</b>	dB	52	60	55	56	63	48	50	49	
<b>Statika</b>										
Betono sluoksnio storis	cm	9	20	12	13	18	12	12	15	
Betono plotas	cm <sup>2</sup> /m	694	1432	871	958	1334	786	814	1050	
Tinkuotos sienos masė	kg/m <sup>2</sup>	275	500	310	354	452	350	380	450	48*
Netinkuotos sienos atsparumo ugniai klasė		A2	A2	A2	A2	A2	A2	A2	A2	A2
Blokų poreikis	vnt/m <sup>2</sup>	8	8	8	8	8	8	8	8	8
Užpilamo betono poreikis	l/m <sup>2</sup>	0,75	155	93	104	143	90	90	135	
Betono armatūros poreikis (orentacinis)	kg/m <sup>2</sup>	2,5	3	3	3	3	3	3	3	
Darbo laikas be betono paruošimo	min/m <sup>2</sup>	45	45	45	45	45	60	60	60	20
Kaina be PVM už vnt	EUR/m <sup>2</sup>	<b>1,67</b>	<b>3,33</b>	<b>2,48</b>	<b>2,66</b>	<b>2,92</b>	<b>4,50</b>	<b>5,62</b>	<b>9,34</b>	<b>2,81</b>
Kaina be PVM už m <sup>2</sup>	EUR/m <sup>2</sup>	<b>13,32</b>	<b>26,62</b>	<b>19,84</b>	<b>21,24</b>	<b>23,34</b>	<b>36,02</b>	<b>44,98</b>	<b>74,70</b>	<b>22,44</b>

